

PS-3260**2.1 VOC European Overall Clearcoat****DESCRIPTION**

PS-3260 is an overall version of PS-3250 which utilizes the same activators. PS-3260 is excellent for overall work and for force dry application. This clearcoat is compliant in all 50 states as well as Canada and features great flow and leveling. Ideal for producing a deep, long-lasting gloss. PS-3260 can be air or forced dried and is a two-full wet coat system.

TECHNICAL PRODUCT INFORMATION

- | | |
|----------------------------|-------------------------|
| • Percent Solids by weight | 41.4% |
| • Pot Life | 1 hour @ 68°F-75°F |
| • Dry Film Thickness | 1 mil per coat (D.F.T.) |
| • Shelf Life | One Year (unopened) |

PACKAGING

- | | | | |
|---------------|-------------------------------------|-----------|--------|
| • PS-3260 | European Urethane Overall Clearcoat | 5 Liter | 2/case |
| • PS-3214-2.5 | Clearcoat Activator Fast | 2.5 Liter | 2/case |
| • PS-3215-2.5 | Clearcoat Activator Medium | 2.5 Liter | 2/case |
| • PS-3216-2.5 | Clearcoat Activator Slow | 2.5 Liter | 2/case |

MIX RATIO

- | | |
|-----------|--|
| • 2 Parts | European Urethane Overall Clearcoat |
| • 1 Part | PS-3214, PS-3215, or PS-3216 Clearcoat Activator |

BASECOAT

- All Acrylic and polyester Basecoat Color Systems that have been catalyzed with basecoat activator.

GUN SETUP

- | | | |
|--------|-------------|----------------|
| • HVLP | 1.3mm-1.4mm | 8-10 psi @ gun |
|--------|-------------|----------------|

APPLICATION

- Apply 2 full wet coats

DRY TIMES

- | | |
|------------------------|--------------------|
| • Air dry | |
| Flash between coats | 10 minutes |
| Dust free | 15 minutes |
| Air dry (to deliver) | 12-16 hours@ 75° F |
| • Express dry | |
| Flash between coats: | 10 minutes |
| Flash before force dry | 10 minutes |
| Cycle time | 30 minutes@ 140° F |

BLENDING

Carefully taper second coat of clear beyond the first. After the final coat of clear, step out the coating by mixing 1 part Blending Clear to 1 part of remaining clear and taper the blend with the resulting mixture.

After the final coat of clear has been blended with the mixture of Blending Clear, further reduce the mixture and use the same gun to finish melting in the edge.

PS-3260**2.1 VOC European Overall Clearcoat****RECOATABILITY / REPAIR**

PS-3260 Clearcoat may be recoated for repair. After cool down when baked.
Air dry repair next day. If recoating after 24 hours, scuff with 1000 grit paper.

SANDING, COMPOUNDING, POLISHING

- Optimum times
Express Dry After cool down
Air Dry 12-16 hours
- Sanding
For dirt removal, lightly nib sand with 1500 grit wet paper and compound.
For best results compound within 24 hours of application.
- Compounding
Using a finishing compound apply a thin ribbon of material to area to be polished. Use a foam polishing pad. Maintain buffer speed at 1200-2000 rpm. Remove excess compound with clean soft cloth before applying polish.
- Polishing
Using a finishing polish and foam polishing pad apply a ribbon of material to work a 2-3 foot square area. Maintain buffer speed at 1000-1600 rpm. Keep buffer moving at all times overlapping approximately 50% each pass. Wipe off excess polish with clean soft cloth. Hand buff with clean soft cloth as a finishing touch.

HEALTH & SAFETY

See Safety Data Sheet and labels for additional safety information and handling instructions.

*The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels and SDS's of all components, since the mixture will have the hazards of all its parts.

*Improper handling and use, for example, poor spray technique, inadequate engineering controls and or lack of Personal Protective Equipment (PPE), may result in hazardous conditions or injury.

*Follow spray equipment manufacturer's instructions to prevent personal injury or fire.

*Provide adequate ventilation for health and fire hazard control.

*Follow company, product SDS and respirator manufacturer's recommendations for selection and proper use of respiratory protection. Be sure employees are adequately trained on the safe use of respirators per company and regulatory requirements.

*Wear appropriate PPE such as eye and skin protection. In the event of injury, see first aid procedures on SDS.

*Always observe all applicable precautions and follow good safety and hygiene practices.

*Safety Data Sheets are available at www.performerseries.com